

# akurit FWR

Moist wall renovation plaster

## Underplaster for temporarily wet plaster and masonry surfaces

standard plastering mortar GP CS II acc. EN 998-1

- mineral
- porous
- sulphate-resistant



## Applications

- for renovation and restoration of moist walls
- as base plaster on plaster and brickwork surfaces, which have been briefly saturated e.g. due to flooding, burst pipe etc.
- as interior plaster for wet rooms, staircases, basements, bathrooms, garages and the like
- for interior and external use

## Properties

- fast-drying thanks to increased pore content
- optimised capillary activity
- vapour diffusion permeable
- entirely mineral-based
- high yield
- good workability
- good stability under load
- economical in use with standard plastering machinery
- feltable

## Composition

- sulphate-resistant cement in accordance with DIN EN 197-1
- calcium hydroxide in accordance with DIN EN 459-1
- graded stone aggregates in accordance with DIN 13139
- additives for regulating and improving workability and product properties

## Substrate

### Suitable substrates

- All types of masonry

### Condition / Testing

- For assessing the plaster primer, VOB/C DIN 18350, Section 3, DIN EN 13914-1/13914-2 as well as the plaster standard DIN 18550-1/18550-2 should be observed.
- The substrate must be load-bearing, clean and free of adhesion-reducing residues.

### Pretreatment

- Old plaster must be removed at least 80 to 100 cm above the visible or adjacent damaged zone up to the masonry.
- Crumbly masonry joints are to be scraped out approx. 2 - 3 cm deep.
- Damaged stones must be replaced.

# akurit FWR

## Moist wall renovation plaster

### Processing

#### Temperature

- Do not process or allow to dry out at air, material or substrate temperatures below +5°C, or if there is a risk of exposure to night frost, or at temperatures above +30°C, or in direct sunlight, or on heated up surfaces, and/or in windy conditions.

#### Mixing / Preparing / Processing

- Suitable for processing by hand, or with conventional plastering machines.
- When machine-processing: Adjust the amount of water accordingly to obtain a workable consistency.
- If the work is interrupted for longer periods, then clean the plastering machine and mortar hoses.
- When mixing manually, first place the quantity of water specified in the technical data in a clean container and then sprinkle in dry mortar. Use clean tap water.
- use a suitable agitator to mix the material until smooth and free of lumps. Leave to rest for a moment and then mix again, adding more water, if required, to achieve the right consistency for applying.
- Do not mix with other products and/or other substances.

#### Applying / Processing / Assembling

- Apply material in layer thicknesses of at least 10 to maximum 20 mm.
- Exterior plaster must have an applied thickness of at least 15 mm.
- On highly or varyingly absorbent substrates, apply two layers, wet in wet.
- Then smooth off the fresh plaster area with suitable tools, e.g. a floating rule, to make it perpendicular and flush.
- Always thoroughly roughen the entire surface of the intermediate layers once the surface has hardened sufficiently. Use a suitable tool such as a lattice plane.
- For a felt-float finish, apply a layer approximately 3 mm thick on the following day, strike off and float finish.
- If the plaster is applied in layers, then allow an intermediate standing time of one day per mm of plaster thickness before applying the next layer.

#### Processing time

- Approx. 2 to 3 hours
- The stated times apply for a temperature of +20°C and relative humidity of 65%.
- Mortar that has already started to harden must never be thinned down with additional water, remixed or applied.

#### Drying / Hardening

- To prevent the plaster from drying out too quickly at higher temperatures, the plastered area should be kept moist for at least three days.
- If the weather conditions are unfavourable (e.g. driving rain, frost, strong sunlight and/or winds), then suitable protection measures must be taken, particularly in the case of freshly coated surfaces.
- Before applying the finish plaster, you must wait at least 1 day per mm of plaster thickness.

#### Subsequent coating / workability

- The plaster surface must be sufficiently hard and completely dried through before coatings are applied. You must wait at least one day per mm of plaster thickness.

#### Tool cleaning

- Clean all tools and equipment with water immediately after use.

#### Notes

- Carefully cover adjacent surfaces and components (e.g. windows, window sills, etc.). Wash off contamination immediately with water.
- For salt-damaged masonry we recommend rehabilitation with a WTA-certified renovation plaster system. Functioning structural waterproofing must be ensured.

### Packaging

- 30 kg/sack
- loose in silo

### Storage

- Store dry and as per instructions.
- If stored in its original packaging, the product will keep for at least 12 months from the date of manufacture.

### Quantity required / Yield

- consumption: approx. 12 kg/m<sup>2</sup> per 10 mm plaster thickness
- yield: app. 25 l fresh mortar per 30-kg-Bag
- yield: app. 830 l fresh mortar per t

# akurit FWR

Moist wall renovation plaster

## Technical Data

<b>Product type</b>	standard plastering mortar GP
<b>Category</b>	CS II
<b>Compressive strength</b>	1.5 - 5 N/mm <sup>2</sup>
<b>Grain</b>	0 – 1 mm
<b>Water requirement</b>	approx. 8.0 l per 30 kg/sack
<b>Set mortar bulk density</b>	approx. 1.6 kg/dm <sup>3</sup>
<b>Fire behaviour</b>	A1 (non-flammable) in accordance with EN 13501
<b>Adhesive tensile strength</b>	≥ 0.08 N/mm <sup>2</sup>
<b>Capillary water absorption</b>	W <sub>c</sub> 2 according to EN 998-1
<b>Water vapour permeability μ</b>	15/35 (table value EN 1745)
<b>Thermal conductivity λ<sub>10,dry,mat.</sub> for P=50%</b>	≤ 0.82 W/(mK)
<b>Thermal conductivity λ<sub>10,dry,mat.</sub> for P=90%</b>	≤ 0,89 W/(mK)

All data are average values that were determined under laboratory conditions according to relevant test standards and application tests. Deviations are possible under practical conditions.

## Safety and disposal instructions

### Safety

- This product produces an alkaline reaction when it comes into contact with moisture/water. Therefore ensure that skin and eyes are protected. If it should come into contact with the skin or eyes, rinse them thoroughly with water. See a doctor immediately if it comes into contact with the eyes.
- Follow further instructions in the safety data sheet.

### GISCODE

- ZP1 (products containing cement, low-chromate)

### Disposal

- Dispose of the material in accordance with the official regulations.
- Completely empty and recycle the packaging.
- Dispose of hardened product in accordance with the local regulations. Do not allow to enter the sewer system. Dispose of the hardened product in the same way as concrete waste and slurries. Waste code according to the Ordinance on the European Waste Catalogue depending on the origin: 17 01 01 (concrete) or 10 13 14 (concreteste and concrete slurries).

## General notes

This information sheet provides only general recommendations. Should you have any queries relating to a specific application, please contact our technical sales advisor or call our hotline: +49 541 601-601. Since natural raw materials are used, the values and properties described may vary somewhat. All of the details given are based on our current knowledge and experience and on the assumption that the materials are professionally applied and used for their normal purpose. All of the details are non-binding and do not release users from their duty to undertake their own tests to ensure suitability for the intended application. Due to the effects of different weather, processing and construction site conditions, no guarantee can be given for the general validity of all details. We reserve the right to make changes as a result of further development of the product and applications engineering. The general rules for construction engineering, the valid standards and guidelines, and the technical working guidelines must be observed. The publication of this technical data sheet renders all previous editions of this data sheet void. Please obtain the latest information from our website.