

akurit MO

Modelling plaster

machine-compatible finish coat for freely-textured or felted textures

Finishing Plaster Mortar CR CS II acc. EN 998-1



Applications

- finish plaster on mineral subsurfaces, for indoor and outdoor applications
- for AKURIT thermal insulation systems
- different textures can be created with different application thicknesses and finishing tools, e. g. smoothed fine plaster, texturing plaster, or country house plaster

Properties

- smooth and easy to process
- suitable for machine application
- high yield
- UV and weather resistant
- water-repellent
- highly water vapour permeable
- behaviour in fire A1 - non-flammable
- mineral

Appearance

- colours: in accordance with ColorPoint 20.10 colour palette

Composition

- white cement in accordance with DIN EN 197-1
- calcium hydroxide in accordance with DIN EN 459-1
- crushed angular Jurassic limestone grain
- finely fractionated silica sand
- additives for regulating and improving workability and product properties
- in case of coloured material: weather-resistant inorganic pigments

akurit MO

Modelling plaster

Substrate

Suitable substrates

- base plasters or reinforcement plasters bound with lime, lime-cement or cement
- gypsum plasterboard and gypsum fibreboard
- normal concrete

Condition / Testing

- The subsurface must be even, dry, clean, load-bearing, absorbent and free of adhesion impairing residues, efflorescence and sinter skins.
- For assessing the plaster primer, VOB/C DIN 18350, Section 3, DIN EN 13914-1/13914-2 as well as the plaster standard DIN 18550-1/18550-2 should be observed.

Pretreatment

- Allow the base plaster to cure for at least one day per mm thickness of base plaster layer before applying the plaster.
- Use on lime, lime cement and cement plaster without primer. Adequately pre-wet base plasters.
- The whole surface of gypsum plasterboards must be primed with akurit GTA Acrylat Tiefengrund. Once this has dried, a coat of akurit GQS Quarz-Sperrgrund must be applied.
- Concrete subsurfaces and gypsum plasters must be pretreated with SCHWENK KG pure or SCHWENK Silica Primer.

Processing

Temperature

- Do not process or allow to dry out at air, material or substrate temperatures below +5°C, or if there is a risk of exposure to night frost, or at temperatures above +30°C, or in direct sunlight, or on heated up surfaces, and/or in windy conditions.

Mixing / Preparing / Processing

- Suitable for processing by hand, or with conventional plastering machines.
- When mixing manually, first place the quantity of water specified in the technical data in a clean container and then sprinkle in dry mortar. Use clean tap water.
- Use a suitable agitator to mix the material until smooth and free of lumps. Leave to develop for a moment and then mix again.
- Do not mix with other products and/or other substances.
- When using colour bags: Sprinkle contents in the water provided and mix evenly. The content of a colour bag corresponds to the amount of colour needed for one sack of dry mortar. Then mix in the material as described.
- When machine-processing: Adjust the amount of water accordingly to obtain a workable consistency.
- If the work is interrupted for longer periods, then clean the plastering machine and mortar hoses.

Applying / Processing / Assembling

- Apply material over the entire surface using an appropriate, non-rusting tool.
- Spray on a thin layer of material using the plastering machine and strike off using suitable, rust-free tools.
- Depending on the texture you require, felt off evenly with a sponge float or model freely with a trowel.

Processing time

- approx. 60 minutes
- The stated times apply for a temperature of +20°C and relative humidity of 65%.
- Mortar that has already started to harden must never be thinned down with additional water, remixed or applied.

akurit MO

Modelling plaster

Drying / Hardening

- To prevent the plaster from drying out too quickly at higher temperatures, the plastered area should be kept moist for at least three days.
- If the weather conditions are unfavourable (e.g. driving rain, frost, strong sunlight and/or winds), then suitable protection measures must be taken, particularly in the case of freshly coated surfaces.
- The drying and hardening process will be slowed down by low temperatures and/or high air humidity and accelerated by high temperatures and/or low air humidity.

Subsequent coating / workability

- Mineral finish plasters must always be given a coat of colour-balancing paint.
- Two coats will be needed on exposed parts of buildings (e.g. the weather side) or if the paint colour differs from the plaster colour.
- The plaster surface must be sufficiently hard and completely dried through before coatings are applied. You must wait at least one day per mm of plaster thickness.

Tool cleaning

- Clean all tools and equipment with water immediately after use.

Notes

- Always apply the plaster “wet in wet” to prevent flaws in the textured finish and avoid the creation of joints. When plastering larger areas, make sure that a sufficient number of skilled workers are deployed.
- In case of facing plaster coloured at the factory, always treat adjacent surface areas with material from the same batch to prevent colour deviations.
- Carefully cover adjacent surfaces and components (e.g. windows, window sills, etc.). Wash off contamination immediately with water.
- Observe the leaflet: “Egalisationsanstriche auf Edelputzen” (Colour-balancing paint on finish plaster) from the Industrieverband WerkMörtel e.V.
- Differences in the texture and/or colour of the finished surface compared to sample areas or colour charts may occur.
- In the case of washed out plaster textures or finish plasters with a grain size less than 2 mm, we recommend an additional reinforcement plaster layer with textile inlay across the entire area in order to reduce the risk of cracking. The same applies in the case of colouring with a lightness value of less than 20.

Packaging

- 25 kg/sack

Storage

- Store sacks appropriately and in dry conditions on pallets.
- If stored in its original packaging, the product will keep for at least 12 months from the date of manufacture.

Quantity required / Yield

- consumption: app. 1,5 kg/m² per 1 mm application thickness
- yield: app. 18 l fresh mortar per 25-kg-Bag

Technical Data

Product type	Finishing Plaster Mortar CR
Category	CS II
Compressive strength	1.5 - 5 N/mm ²
Grain	
Water requirement	approx. 6.0 l per 25 kg/sack
Set mortar bulk density	approx. 1.35 kg/dm ³
Fire behaviour	A1 (non-flammable) in accordance with EN 13501
Adhesive tensile strength	≥ 0.08 N/mm ²
Capillary water absorption	W _c 2 according to EN 998-1
Water vapour permeability μ	15/35 (table value EN 1745)
Thermal conductivity λ_{10,dry,mat.} for P=50%	≤ 0.82 W/(mK)
Thermal conductivity λ_{10,dry,mat.} for P=90%	≤ 0,89 W/(mK)

All data are average values that were determined under laboratory conditions according to relevant test standards and application tests. Deviations are possible under practical conditions.

akurit MO

Modelling plaster

Safety and disposal instructions

Safety

- This product produces an alkaline reaction when it comes into contact with moisture/water. Therefore ensure that skin and eyes are protected. If it should come into contact with the skin or eyes, rinse them thoroughly with water. See a doctor immediately if it comes into contact with the eyes.
- Specifications regarding the classification and labelling of the product can be found in the safety data sheet at www.quick-mix.de.

GISCODE

- ZP1 (products containing cement, low-chromate)

Disposal

- Dispose of the material in accordance with the official regulations.
- Completely empty and recycle the packaging.
- Dispose of hardened product in accordance with the local regulations. Do not allow to enter the sewer system. Dispose of the hardened product in the same way as concrete waste and slurries. Waste code according to the Ordinance on the European Waste Catalogue depending on the origin: 17 01 01 (concrete) or 10 13 14 (concretewaste and concrete slurries).

General notes

This information sheet provides only general recommendations. Should you have any queries relating to a specific application, please contact our technical sales advisor or call our hotline: +49 541 601-601. Since natural raw materials are used, the values and properties described may vary somewhat. All of the details given are based on our current knowledge and experience and on the assumption that the materials are professionally applied and used for their normal purpose. All of the details are non-binding and do not release users from their duty to undertake their own tests to ensure suitability for the intended application. Due to the effects of different weather, processing and construction site conditions, no guarantee can be given for the general validity of all details. We reserve the right to make changes as a result of further development of the product and applications engineering. The general rules for construction engineering, the valid standards and guidelines, and the technical working guidelines must be observed. The publication of this technical data sheet renders all previous editions of this data sheet void. Please obtain the latest information from our website.